

IN THE SPECIFICATION:

Revise Page 15, lines 2-14 to read as follows:

- - A plain weave fabric with 30d-18 40f polyester multifilament yarn (composed of singlefilament with a W-shaped cross-section, whose circumscribed rectangle has a long side (L) of $35\mu\text{m}$ and a short side (S) of $15\mu\text{m}$ -Asahi Chemical-made Technofine) for its warp and 50d-30f polyester multifilament yarn (composed of singlefilament with a W-shaped cross-section, whose circumscribed rectangle has a long side (L) of $35\mu\text{m}$ and a short side (S) of $15\mu\text{m}$ -Asahi Chemical-made Technofine) for its weft was scoured, dried and heat-preset before being caustic treatment for weight reduction by 10% to convert the fabric into one with a warp density of 149 yarns/inch, a weft density of 138 yarns/inch and a cover factor of 1792. - -.